## WEICONLOCK<sup>®</sup> AN 302-80 Pipe and thread sealing





# Pipe and thread sealing for passive materials | drinking water approval

Pipe and thread sealing for passive materials

Techr	iische	Daten

Colour		green
For thread connections up to		M 36
Gap bridging up to max.		0,2 mm
Breakaway torque		15 - 20 Nm
Prevail torque		25 - 30 Nm
Shear strength Nmm <sup>2</sup> (DIN 54452)		20 - 30 N/mm²
Handling strength	at room temperature	5 - 10 min.
Final strength	(100 % strength)	6-12 h
Temperature resistance		-60°C to +200°C
IMPA Code		450805
ISSA Code		53.402.05

### WEICONLOCK® Anaerobe Kleb- und Dichtstoffe

#### Surface pre-treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

#### Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. Apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. When used as flange sealing, apply a continuous bead to one flange side, then assemble parts quickly and screw tight. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

#### Storage

WEICONLOCK has a shelf life of at least 24 months, when stored at room temperature in closed original container. Protect from heat sources and direct sunlight. The air contained in the Pen keeps WEICONLOCK liquid.

#### Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

#### Accessories

30700200 Activator F, 200 ml, green 30955172 Dosing Tip, 1 PCE

#### Available sizes:

30280200	WEICONLOCK <sup>®</sup> AN 302-80 Pipe and thread
	sealing, 200 ml, green
30280020	WEICONLOCK <sup>®</sup> AN 302-80 Pipe and thread
	sealing, 20 ml, green WEICONLOCK <sup>®</sup> AN 302-80 Pipe and thread
30280150	WEICONLOCK <sup>®</sup> AN 302-80 Pipe and thread
	sealing, 50 ml, green

To the product detail



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarante the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

EICON Inc. Canada phone +1 877 620

8889 info@weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr